

CALPICO, INC

# CALPICO, INC

P: 650-588-2241

F: 650-873-6952

#1003 ASBESTOS FREE DUCT SEALING COMPOUND

## Features and Benefits

FDA Approved: As listed in CFR, Title 21, being composed of ingredients acceptable for packaging and transporting food

U.S.D.A. Acceptable: Chemically acceptable to the U.S.D.A. for use in meat and poultry processing areas under Federal Inspection.

Dielectric Strength: Aprox. 100 volts per mil (ASTM D149-64). Resistivity: 1.5.1 @ 100 degrees C. 4.8 x 10 ohm-cm 1.5.2 after 96 hrs @ 115 degrees 4.8 x 10 (ASME power test code of 1965, Section 4.05).

Chemical Resistance Excellent resistance to water, alcohols, mild acids and bases.

Vehicle Bleedout: None

Non-Corrosive: Will not corrode Metals.

Non-Irritant: No irritation to eyes or skin as listed in CFR, Title 16, "Appraisal of the safety of chemicals in food, drugs, and cosmetics.

Paintability: Yes.

**DESCRIPTION:** #1003 Asbestos Free Sealer is a gray permanently soft, non-toxic compound which will adhere to most clean dry surfaces. #1003 Asbestos free Sealer will not adversely affect other plastic materials or corrode metals. It also has no adverse effect to human skin.

**USES:** #1003 Sealer is used primarily by the building and specifically by the electrical trade to seal around electrical boxes, flashings, and service mast entries, etc. It can be shaped by hand to any form and reused if necessary. #1003 has countless other applications in the refrigeration, heating and cooling, plumbing, and metal fabrication fields as well as being an excellent general purpose sealant around the home. #1003 may be painted immediately after application and will not bleed through the dry paint.

**FORMS:** #1003 Sealer is individually wrapped and placed in plastic bags with convenient reusable clips to seal out dirt and moisture that might contaminate the product. #1003 Sealer is available in one and five pound packages, packed by fifty pound net per carton. Also in bulk upon request.

PROPERTIES	TEST METHOD	VALUE
Base		Non-Drying synthetic polymers and oils
Filters		Saturated mineral fillers and other inert ingredients
Specific Gravity	ASTM D71-72	1.65 to 1.7
Cone Penetration	ASTM D217-52T	Load of 300 gm. 5 sec @ 25 degrees F, 100-115 mm/10
Temperature usage range	25 degrees F to + 120 degrees F	Recommended
Temperature tolerance range	-30 degrees F to +175 degrees F	Will not slump at +275 degrees F